



UNIVERSITI PUTRA MALAYSIA

**PROPERTIES AND UTILISATION OF TROPICAL BAMBOO
(*GIGANTOCHLOA SCORTECHINII*), FOR STRUCTURAL PLYWOOD**

MOHD KHAIRUN ANWAR BIN UYUP

FH 2003 11

**PROPERTIES AND UTILISATION OF TROPICAL BAMBOO
(*GIGANTOCHLOA SCORTECHINII*), FOR STRUCTURAL PLYWOOD**

By

MOHD KHAIRUN ANWAR BIN UYUP

**Thesis Submitted to the School of Graduates Studies, Universiti Putra Malaysia,
in Fulfilment of the Requirement for the Degree of Master of Science**

March 2003



Specially dedicated to:
My beloved late mother
SITI ESAH BT YASIN
(Al-Fatihah)

Your love always in my heart

Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfilment of the requirement for the degree of Master of Science

**PROPERTIES AND UTILISATION OF TROPICAL BAMBOO
(*GIGANTOCHLOA SCORTECHINII*), FOR STRUCTURAL PLYWOOD**

By

MOHD KHAIRUN ANWAR BIN UYUP

March 2003

Chairman: Associate Professor Zaidon Ashaari, Ph.D.

Faculty: Forestry

The objectives of these study were to determine the physical and mechanical properties of 4-year-old *Gigantochloa scortechinii* culms and to evaluate the properties of plywood manufactured from the bamboo culms. Bamboo culms were split using hand splitter to produce splits. Strips were prepared by removing the epidermis and the inner skin using knife, whereas outer splits were prepared by removing the inner skin of the culm. For the bamboo plywood production, the bamboo strips were glued edge-to-edge using polyvinyl acetate resin into a 410 mm x 410 mm x 4 mm sized laminate. The laminates were then bonded perpendicularly to each other using phenol formaldehyde resin to produce three-ply bamboo plywood. The assembly time was set at 30 min and bamboo plywood was consolidated by hot pressing at 140°C and pressure of 14 kg/cm² for 6.5 minutes. Commercial structural plywood (Grade A) Merawan species with the same thickness as the bamboo plywood (12 mm) was used for comparison purposes.

The results of the physical studies indicate that within the culm wall, the moisture content decreased from the interior towards the peripheral layer of the culm while the specific gravity increased. The moisture content decreased with height, whilst specific gravity increased. In the strip form, bamboo shrank more in both radial and tangential directions than in the longitudinal direction. Between radial and tangential, shrinkage occurs more in radial than in tangential. The mean value of modulus of rupture (MOR) for the bamboo strips (179.6 N/mm^2) showed no significant difference with splits (periphery layer oriented upward, 158.3 N/mm^2) but a significant difference was observed when compared with the periphery layer oriented downwards (134.2 N/mm^2).

The bonding strength of bamboo plywood meets the minimum requirement of Malaysian Standard (MS 228:1991 UDC674-419.23). The dry shear strength was in the range of 3.1 to 3.4 N/mm^2 and the bamboo failure between 44 to 66%. In comparisons to commercial plywood, the MOR, modulus of elasticity (MOE) and compression parallel to grain of the bamboo plywood were significantly higher. The values were 65.4 vs. 42.0 N/mm^2 for MOR and 8955 vs. 4583 N/mm^2 for MOE and 35.4 vs. 19.9 N/mm^2 . Specific strength values (strength/density) were also higher for bamboo plywood than for commercial plywood. After 24 hours of soaking in water, the linear expansion perpendicular to the grain and thickness swelling of the bamboo plywood were markedly higher than that of the commercial plywood, i.e. respectively 1.51% and 0.43% for the former and 5.44% and 4.42% for the latter. Water absorption did not differ significantly between both types of plywood 33.9% and 35.9% in the bamboo plywood and commercial plywood respectively.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia bagi memenuhi syarat untuk memperolehi keperluan untuk ijazah Master Sains

CIRI-CIRI DAN PENGGUNAAN BULUH TROPIKA (*GIGANTOCHLOA SCORTECHINII*), UNTUK PAPAN LAPIS STRUKTUR

Oleh

MOHD KHAIRUN ANWAR BIN UYUP

March 2003

Pengerusi: Profesor Madya Zaidon Ashaari, Ph.D.

Fakulti: Perhutanan

Objektif penyelidikan ini ialah mengenalpasti sifat fizikal dan mekanikal buluh semantan (*Gigantochloa scortechinii*) serta sifat buluh lapis yang dihasilkan daripada buluh ini. Bagi sifat-sifat buluh semantan, buluh dipecah menggunakan pemecah buluh bagi menghasilkan bilahan kemudian kulit luar dan dalam dibuang dengan menggunakan pisau. Dalam pembuatan buluh lapis, bilah buluh dilekatkan dengan PVAc dibahagian tepi bagi menghasilkan sekeping lapisan (410 mm x 410 mm x 4 mm) kemudian digam dengan menggunakan fenol formaldehyde. Masa pembuatan ialah selama 30 minit dan suhu penekan panas ialah 140°C dengan tekanan 14 kg/m³ selama 6.5 minit. Sebagai perbandingan papan lapis (grade A) daripada sepsis Merawan digunakan bagi membandingkan kekuatan fizikal dan mekanikal.

Keputusan daripada sifat fizikal didapati kandungan lembapan menurun daripada dalam ke bahagian luar tebal buluh manakala ketumpatan bertambah. Kandungan lembapan

menurun dengan ketinggian buluh semantan tetapi ketumpatan meningkat. Dalam bentuk bilah (tanpa kulit luar dan dalam) ia mengecut lebih pada bahagian radial dan tangen berbanding longitud. Perbandingan antara arah radial dan tangen menunjukkan buluh Semantan mengecut lebih pada arah tangen. Nilai purata bagi kekuatan kenyalan untuk bilah (179.6 N/mm^2) tidak menunjukkan sebarang perbezaan dengan bilahan dalam bentuk asal (158.3 N/mm^2). Tiada perbezaan wujud apabila bilah diuji dengan meletakkan kulit ke atas atau ke bawah tetapi nilai menunjukkan ia lebih tinggi.

Kekuatan lekatan buluh lapis telah mencapai piawaian minimum dalam Malaysia Standard (MS 228). Ujian dalam keadaan kering memberikan nilai dalam lingkungan $3.1 - 3.4 \text{ N/mm}^2$ dan purata peratus kegagalan buluh pula ialah diantara 44 - 66%. Apabila dibandingkan dengan papan lapis komersial, kekuatan kenyalan, modulus kenyalan dan tekanan menunjukkan buluh lapis lebih kuat. Nilainya ialah 65.4 berbanding 42.0 N/mm^2 , 8955 berbanding 4583 N/mm^2 dan 35.4 berbanding 19.9 N/mm^2 . Nilai kekuatan spesifik (kekuatan / isipadu) adalah lebih tinggi bagi buluh lapis. Selepas 24 jam direndam dalam air, kadar pengembangan arah bertentangan dengan ira dan tebal adalah lebih tinggi berbanding papan lapis komersial dengan nilai 1.51 berbanding 0.43% dan 5.44 berbanding 4.42% . Manakala kadar resapan bagi kedua-dua produk ini tiada beza, 33.9 dan 35.9% .

ACKNOWLEDGEMENTS

Praise to God the Mighty for without Him I would not be born in this world and complete this research. Special notes of gratitude to my main supervisor Prof. Madya Dr. Zaidon Ashaari for never losing his patience or humour and for never losing track of me. To all committee members; Dr. Razak Wahab (FRIM), Dr. Paridah Md. Tahir and Dr. Wong Ee Ding, thank you very much for the guidance.

Special thanks to Forest Research Institute of Malaysia (FRIM); to Mr. Hamdan Hussin for the assistance given and to whom I seek for answers when I couldn't find them anywhere especially to Mr. Saimin, Mr. Hashim, Mr. Wan Tarmeze, Mr. Omar, Mr. Tamizi, Dr. Tan, Abang Rahim, Sufian and others. My thanks also go to the staff at the Faculty of Forestry, Universiti Putra Malaysia especially to Mr. Baharom, Kak Aida and Kak Azimah.

I wish to also express my appreciation to Malaysian Adhesive and Chemical Sdn. Bhd (Cik Nor Yuziah), Casco Adhesive Sdn. Bhd (En. Haris), my cousin Saharuddin and wife, my friends (Kamal, Zamri, Helmi, Nizam, Samat, Huslizam, Zulkifli, Saiful Azly, Fariz, Rashidi, Mirzan, Azam, Syirfan and Azrul Nizam) and many others for their enduring friendships and support. To my brothers (M. Khairul Najmi, M. Khairul Naim, M. Khairul Azree, M. Khairul Fahmy) and fiancée, Suhana, your love has kept me going on. We have come a long way together. Last but not the least, to my parents (Uyup bin Hj. Siam and Sarol Bariah) who always give me support when I feel give up.



I certify that an Examination Committee met on 20th March 2003 to conduct the final examination of Mohd Khairun Anwar Bin Uyup on his Master of Science thesis entitled “Properties and Utilisation of Tropical Bamboo (*Gigantochloa scortechnii*) for Structural Plywood” in accordance with Universiti Pertanian Malaysia (Higher Degree) Act 1980 and Universiti Pertanian Malaysia (Higher Degree) Regulations 1981. The committee recommends that the candidate be awarded the relevant degree. Member of the Examination Committee are as follows:

MOHD ZIN JUSOH

Associate Professor
Faculty of Forestry
Universiti Putra Malaysia
(Chairman)

ZAIDON ASHAARI, Ph.D.

Associate Professor
Faculty of Forestry
Universiti Putra Malaysia
(Member)

RAZAK WAHAB, Ph.D.

Head of Non-Wood Forest Products
Forest Research Institute of Malaysia
(Member)

PARIDAH MOHD TAHIR, Ph.D.

Associate Professor
Faculty of Forestry
Universiti Putra Malaysia
(Member)

WONG EE DING, Ph.D.

Faculty of Forestry
Universiti Putra Malaysia
(Member)



GULAM RUSUL RAHMAT ALI, Ph.D.

Professor/ Deputy Dean
School of Graduate Studies
Universiti Putra Malaysia

Date: 18 JUL 2003

This thesis submitted to the Senate of Universiti Putra Malaysia has been accepted as fulfilment of the requirements for the degree of Master of Science. The members of the Supervisory Committee are as follow:

ZAIDON ASHAARI, Ph.D.

Associate Professor
Faculty of Forestry
Universiti Putra Malaysia
(Chairman)

RAZAK WAHAB, Ph.D.

Head of Non-Wood Forest Products
Forest Research Institute of Malaysia
(Member)

PARIDAH MOHD TAHIR, Ph.D.

Associate Professor
Faculty of Forestry
Universiti Putra Malaysia
(Member)

WONG EE DING, Ph.D.

Faculty of Forestry
Universiti Putra Malaysia
(Member)



AINI IDERIS, Ph.D.

Professor/ Deputy Dean
School of Graduate Studies
Universiti Putra Malaysia

Date: 15 AUG 2003

DECLARATION

I hereby declare that the thesis is based on my original work except for quotations and citations, which have been duly acknowledge. I also declare that it has not been previously or concurrently submitted for any other degree at UPM or other institutions.



MOHD KHAIRUN ANWAR BIN UYUP

Date: 2 May 2003

TABLE OF CONTENTS

	Page
DEDICATION	ii
ABSTRACT	iii
ABSTRAK	v
ACKNOWLEDGEMENTS	vii
APPROVAL SHEETS	viii
DECLARATION FORM	x
TABLE OF CONTENTS	xi
LIST OF TABLES	xiv
LIST OF FIGURES	xvi
LIST OF PLATE	xviii
 CHAPTER	
1 INTRODUCTION	1
 2 LITERATURE REVIEW	
Bamboo in Peninsular Malaysia	5
Genus <i>Gigantochloa</i>	6
Distributions and Commercial Bamboo	7
Properties of Bamboo	
Anatomical Structure	8
Physical Properties	10
Mechanical Properties	11
Natural Durability	14
Uses of Bamboo in Malaysia	15
Traditional Uses	15
Value Added Products	16
Potential Bamboo Products	18
Bamboo Composites	18
Bamboo Plywood	19
Adhesives	20
 3 PHYSICAL AND MECHANICAL PROPERTIES OF GIGANTOCHLOA SCORTECHINII	
Introduction	22
Objectives	24
Preparation of Materials	24
Evaluation of Physical Properties	31
Sample Preparation	31
Green Moisture Content	33
Specific Gravity	34



Shrinkage	35
Evaluation of Mechanical Properties	35
Static Bending	37
Compression Parallel to Grain	39
Statistical Analysis	40
Results and Discussion	
Evaluation of Physical Properties	41
Evaluation of Mechanical Properties	52
Conclusion	58
4 BONDING PROPERTIES OF <i>GIGANTOCHLOA SCORTECHINII</i>	
Introduction	59
pH and Buffering Capacity of Wood	61
Phenol Formaldehyde and Polyvinyl Acetate Resins	62
Objectives	64
Evaluation of Bonding Properties	
Contact Angle of Wettability	64
Buffering Capacity	65
Viscosity of the Glue Mix	66
Bonding of <i>Gigantochloa scortechinii</i>	67
Plywood Shear Test	68
Results and Discussion	
Contact Angle of Wettability	68
Buffering Capacity of <i>Gigantochloa scortechinii</i>	70
Adhesive Formulation	74
Glue Bond Quality	76
Conclusions	80
5 BAMBOO PLYWOOD FROM <i>GIGANTOCHLOA SCORTECHINII</i>	
Introduction	81
Objectives	82
Material and Methods	
Preparation of Bamboo Strips	82
Bamboo Sheet (bamboo veneer) Manufacturing	84
Glue Spreading	85
Cold and Hot Pressing	86
Cutting of Specimens	88
Mechanical Properties Test	
Static Bending	90
Compression Parallel to Grain	93
Physical Properties Test	
Moisture Content	94
Density	95
Dimension stability	95

	Water Absorption	97
	Statistical Analysis	97
	Results and Discussion	
	Evaluation of Mechanical Properties	98
	Evaluation of Physical Properties	103
	Conclusion	107
6	OVERALL CONCLUSION AND RECOMMENDATION	
	Conclusion	108
	Recommendations	110
	REFERENCES	112
	APPENDIX	125
	VITA	128

LIST OF TABLES

Table	Page
1 Comparison of strength and stiffness of building materials	12
2 Mechanical properties of bamboo and timber species of different countries	13
3 Natural durability of some bamboo species (grave-yard test)	15
4 Types of products and the respective bamboo species used in bamboo based industry in Peninsular Malaysia	17
5 Bending strength of bamboo and wooden platform boards	20
6 The basic characteristics of 4 year-old <i>Gigantochloa scortechinii</i> extracted from bamboo plantation at Nami, Kedah and Forest Research Institute of Malaysia (FRIM), Selangor	28
7 Specimens dimensions of bamboo splits and strips for evaluation of physical and mechanical properties	32
8 Physical properties of 4-year-old <i>G.scortechinii</i> extracted at FRIM, Selangor	42
9 Green moisture content and specific gravity of some species of bamboo	42
10 Mechanical properties of 4 year-old <i>G. scortechinii</i>	53
10 Mechanical properties of some bamboo species	53
11 Properties of adhesive mixture for gluing of <i>G. scortechinii</i>	67
12 Contact angle ($^{\circ}$) of <i>G. scortechinii</i> using Face Contact Anglemeter	69
13 Average value of glue line shear strength and wood failure for different glue mix and assembly times	77
14 Shear strength of some plywood in dry condition	76
15 Summary of analysis of variance on shear strength properties of <i>G. scortechinii</i> bamboo plywood	79
16 Mechanical properties of bamboo plywood and merawan plywood	98



17	Dimensional stability and water absorption of bamboo plywood and merawan plywood during short and long term soaking	105
----	---	-----

LIST OF FIGURE

Figure	Page
1 A: Definition of basal, middle and top portions of bamboo culms B: Preparation of test specimens from the basal portion	27
2 Preparation of samples for physical properties evaluation	32
3 Schematic diagram for the preparation of samples for shrinkage evaluation	33
4 Schematic diagram for the preparation of samples for mechanical properties evaluation	35
5 Direction of loading for strips and splits in the static bending test	38
6 Moisture content of 4-year-old <i>Gigantochloa scortechinii</i> along the culms	45
7 Relationship between moisture content and culm wall thickness of 4-year old <i>G.scortechinii</i>	46
8 Distribution of specific gravity of 4-year-old <i>Gigantochloa scortechinii</i> along the culms	48
9 Relationships between specific gravity and culm wall thickness of 4-year-old <i>G.scortechinii</i>	49
10 The bamboo and wood cell	51
11 Variability of fibres across the culm wall in <i>Phyllostachys makinoi</i> (Liese, 1998)	54
12 Variation in pH with respects additions of alkali	71
13 Variation in pH with respects addition of acid	71
14 Schematic representation of an adhesive joint, showing the various “links” in the chain analogy (Marra, 1964)	72
15 Viscosity of phenol formaldehyde glue mix	75
16 Processing sequence for the production of bamboo plywood	87
18 Cutting pattern of specimens for mechanical and physical testing	88

19	Schematic diagram of static bending test for bamboo plywood	92
20	Measurements of thickness swelling and linear expansion (parallel and perpendicular to grain).	96



LIST OF PLATES

Plate		Page
1	Distribution of vascular bundles of <i>Gigantochloa scortechinii</i> (Anon, 1999)	9
2	<i>Gigantochloa scortechinii</i> clumps	25
3	Harvesting of bamboo	26
4	Air-drying of bamboo culms in the laboratory	29
5	Hand splitter	29
6	Static bending test	38
7	Compression parallel to grain	40
8	Distribution of vascular bundles structure at the internode 6 th and 14 th of 4 -year-old <i>Gigantochloa scortechinii</i>	44
9	Mode of failure in bending test for strips with different angle with span parallel to grain:-	
	(a) Compression at the top	55
	(b) Splintering tension at bottom	56
10	Compression failure (splintering tension) in bending for splits with periphery upwards	56
11	Mode of failure in bending test for splits with periphery downwards	57
12	Common mode of failure type in compression parallel to grain	57
13	A Face Contact Anglemeter	65
14	Bamboo failure of <i>G.scortechinii</i> bamboo plywood	73
15	Penetration of adhesive in the cross section of the core layer of bamboo plywood (100 X)	78
17	Sizing and splitting of bamboo culm	83
18	Single face-planing machine	84
19	A clamping jig used to clamp the bamboo strips	85



CHAPTER 1

INTRODUCTION

Bamboo is a cultural feature of the Asia region. Its plethora of essential uses has led to the use of terms such as “bamboo culture”, “green gold”, “poor man’s timber”, “bamboo friend of the people” and “the cradle coffin timber” (Tewari, 1992). Bamboo is also known as “the wood of the poor” in India, “the friend of the people” in China and “the brother” in Vietnam (Farrelly, 1984). Malaysia has more than 50 species of bamboo, 25 of them are indigenous, while the rest are known exotic. Genera that can be found in Malaysia are *Bambusa*, *Dendrocalamus*, *Gigantochloa*, *Chusquea*, *Dinochloa*, *Melocanna*, *Phyllostachys*, *Racemobambos*, *Schizostachyum*, *Thyrsostachys* and *Yushania*. (Wong, 1995).

The three species, which are the most widespread in Peninsular Malaysia, are *Gigantochloa scortechinii* (the most useful species), *Dendrocalamus pendulus* and *Scizostachyum grande* (Azmy, 1998). These species grows naturally in the foothills and valleys of series of mountain ranges that stand up most prominently in the northern half of the peninsular Malaysia, including the two most massive, viz., the Main Range, running from Pattani in Thailand to Malacca on the southwest coast, and the Terengganu Highlands, at the northeastern flank of the peninsula up to about 1200 m (Wong, 1995).

Bamboo in its natural form are mainly used as construction material such as floors, walls and other household items and utensils. Therefore bamboo becomes a forefront as one of the most easily available resources within the rural communities. This is proven in several Southeast Asian and East Asian countries where the value of bamboo is extremely high if proper techniques are developed at processing and manufacturing stages (Salleh & Wong, 1987). In China, bamboo becomes more interesting and practical as substitute for timber because of their poor forest resources (Zhu, 1987).

In Malaysia, only 14 species have been used intensively in bamboo industry for making poultry cage, vegetable basket, incense stick and joss paper industry, skewer and chopstick, sunblind weaving industry and commercial handicraft (Azmy et al. 1994; Aminuddin, 1995). Due to its fast growth, availability, attractive and unique appearance as well as toughness, this material can be converted into engineered products such as laminated boards (Abd. Latif et al. 1989). However, in most bamboo producing countries, the techniques for bamboo processing are primitive and the products are low in quality (Zhu, 1995).

In China and Japan, bamboo composites and parquet products from bamboo have gained commercial importance and have been widely used as engineering structural material (Tang, 1996). Bamboo plywood is a panel consisting of an assembly of plies of bamboo sheets bonded together with a resin with the direction of the grain in alternate plies at right angles (Chen, 1987). There are three types of bamboo

plywood: bamboo mat plywood, bamboo curtain plywood and laminated board. (Zhang, 1992).

Today, bamboo product has become more popular not only in India and China but also in Europe and America. Bamboo is regarded as eco friendly and can be used as an alternative to timber. The world is loosing its resource of wood due to higher demand and to recover the resources will take 15 to 20 years. Bamboo, due to its early maturity has potential to be used as an alternative material for wood. Many researchers agreed that the suitable age of the bamboo used is 3 to 4 years old (Thammicha, 1989; Abd. Latif et al. 1990; Jamaluddin, 1999). In Malaysia, the properties of laminated bamboo, cement bonded bamboo particleboard and bamboo particleboard have been evaluated (Razak et al.1997; Jamaluddin et al. 1999; Chew et al.1992). However before this can be achieved, a study need to be carried out to evaluate the properties of bamboo plywood. The need to understand the physical and mechanical properties of bamboo strips and splits forms. Hence, the 4-year-old *G. scortechinii* was chosen as raw material due to its availability and the its characteristics itself.

The objective of this study was to evaluate the suitability of *Gigantochloa scortechinii* as a raw material for structural bamboo plywood. This study aims to:

1. Determine the physical and mechanical properties of *G. scortechinii* strips (without periphery and inner skin) and splits (with periphery intact).
2. Evaluate the adhesion characteristics of *G. scortechinii* and its compatibility to phenolic resin
3. Assess the properties of bamboo plywood manufactured from *G. scortechinii*.

CHAPTER 2

LITERATURE REVIEW

Bamboo in Peninsular Malaysia

Bamboo is a unique group of giant arborescent grasses, in which the wood culms arise from rhizome (Thammicha, 1989). Current knowledge lists about 75 genera and 1250 species of bamboo. About 75% of these species are used locally for one or many purposes, and about 50 species are used extensively (Rao et al. 1998). Bamboo plays a very important role on the life of the rural people and now is more important economically, due to the development of several industries using bamboo as raw materials (Widjaja, 1991).

There are 14 genera and 59 species of bamboo in Peninsular Malaysia. Four of these genera (*Chimonobambusa*, *Melocanna*, *Phyllostachys* and *Thyrsostachys*) are not native of Peninsular Malaysia (Wong, 1995). The bamboo species are grouped under genera *Bambusa*, *Chusque*, *Dendrocalamus*, *Dinochloa*, *Gigantochloa*, *Melocanna*, *Phyllostachys*, *Racembambos*, *Schizostachyum*, *Thyrsostachys* and *Yushania*. From the total of 59 bamboo species only 14 are commercially utilized while the rest are left idle in their habitat, mainly due to the with lack of knowledge on their properties and potential usage (Abd. Razak & Abd. Latif, 1995).

Genus *Gigantochloa*

Gigantochloa scortechinii is the most common type of bamboo found wild in the forest (Azmy & Abd. Razak, 1991). There are 13 species of *Gigantochloa* in Peninsular Malaysia. The species are *Gigantochloa albopilosa*, *G. rideleyi*, *G. hasskarliana*, *G. latifolia*, *G. ligulata*, *G. albovestita*, *G. rostrata*, *G. thoi*, *G. scortechinii*, *G. holtumiana*, *G. wrayi* and two other species only known as *Gigantochloa spp* (Wong, 1995). The culms of *Gigantochloa* usually have short branches at the nodes (Dransfield, 1980), and most species of *Gigantochloa* are useful for local people and are planted for everyday use in villages.

The culm sheaths green at the very base and flushed intense orange towards the top, covered with the dark brown to black hairs. The culms height usually achieves 20 meter tall, diameter of between 6 –12 cm and internodes length of 30 – 40 cm long (Wong, 1995). Azmy (1998) reported that the culm wall thickness ranges from 11 – 15 mm and young bamboo shoots grows vertically. The size of the culms varies from species to species. They can be as large as 20 cm in diameter and as tall as 30 m (Dransfield, 1980). This type of bamboo is considered as large diameter bamboo (Azmy & Abd. Razak, 1991). Azmy (1998) also added that the matured bamboo could be identified by the colour of bamboo while the young culm is usually covered with a fine white waxy powder (Abd. Razak & Abd. Latif, 1995). *Gigantochloa* can be recognized by the straight culms, the absence of prominent auricles on the culm sheaths and the long blade of the culm sheath (Azmy and Razak, 1991).